

# Jon-Wood®



## Waterborne Wood Floor Finish

*Specifically formulated for professional use on maple sport floors, providing a tough, high-build urethane finish.*

### Highly Durable

Jon-Wood™<sup>MFC</sup> Waterborne Wood Floor Finish will provide excellent durability, chemical resistance and protection against perspiration and routine cleaning.

### Non-Yellowing Finish

Jon-Wood™<sup>MFC</sup> Waterborne Wood Floor Finish will stay clean and clear even after several recoats.

### Fast-Drying Finish

Can apply second coat of finish after approximately 2-3 hours. Allow final coat to dry 48 hours before using floors.

### Gloss Retention

Jon-Wood™<sup>MFC</sup> Waterborne Wood Floor Finish is formulated to retain its gloss throughout the year.



**Johnson wax**  
**PROFESSIONAL**

# Jon-Wood<sup>TM/MC</sup>

## WATERBORNE WOOD FLOOR FINISH

### Profile

<b>WHAT IS IT?</b>	A premium two-component waterborne wood floor finish specifically formulated for professional use on maple sport floors, providing a tough, high-build urethane finish.
<b>WHAT DO I USE IT ON?</b>	Use on all types of maple wood floors.
<b>HOW DO I USE IT?</b>	Properly abrade and coat floors with Jon-Wood <sup>TM/MC</sup> Recoat Adhesion Formula prior to use. See product label for complete instructions.
<b>PRECAUTIONS</b>	Allow final coat to dry at least 48 hours before use. Allow approximately 7 days for the floor to completely cure. Do not replace walk-off mats until finish is fully cured. Do not clean with water or cleaner during the first week. Avoid contact with skin and eyes. Keep out of reach of children. For commercial and industrial use only.

### Specifications

<b>pH:</b> . . . . .	7.9 – 8.6
<b>Viscosity:</b> . . . . .	(#4 Ford cup @ 25° C) 14.5 – 17.0 seconds
<b>Coverage Rate:</b> . . . . .	500 – 600 sq. ft. / gal
<b>Flash Point:</b> . . . . .	>200° F
<b>Stability:</b> . . . . .	1 year shelf life for unopened container
<b>VOC:</b> . . . . .	<350 gram/L (2.9 lbs. / gal)
<b>Curing Time:</b> . . . . .	24 hrs. – 80%; 72 hrs. – 90%; 1 week – 100%
<b>Non-Volatile Solids:</b> . . . . .	28.0 – 29.5% minimum
<b>Drying Time:</b> . . . . .	2-3 hours
<b>Pot Life:</b> . . . . .	The finish/crosslinker mixture is active for 8 hours after it is mixed. Within 2-3 days, crosslinker may be added one additional time.
<b>Slip Resistance:</b> . . . . .	Meets ASTM D2047 requirements for slip resistance.
<b>HMIS Hazard Ratings:</b>	<b>Concentrate</b>
Health	1
Flammability	0
Reactivity	0

### Safety Reminder

Please make sure your employees read and understand the product label and Material Safety Data Sheet before using this product. The label contains directions for use, and both the label and MSDS contain hazard warnings, precautionary statements and first aid procedures. MSDS's are available on line at [www.johnsondiversey.com](http://www.johnsondiversey.com) or by calling 1-888-352-2249.

### Packaging

PACK / SIZE	PRODUCT CODE
1/5 gallon / 18.9 L pail w/12.7 oz. (375 mL) crosslinker chemical	14676
3/1 gallon / 3.78 L bottle w/2.7 oz. (79.8 mL) crosslinker chemical	14678



**Johnson wax**  
PROFESSIONAL

FOR COMMERCIAL & INDUSTRIAL USE ONLY

© 2003 JohnsonDiversey, Inc., Sturtevant, WI 53177-0902. All Rights Reserved.

*For further information on special applications or other Johnson Wax Professional products, contact your JohnsonDiversey representative, or call us at 1-800-558-2332 or visit our web-site at [www.johnsondiversey.com](http://www.johnsondiversey.com)*